



## STORMFLEX ELITE™

**STORMFLEX ELITE™** is a premium grade, mechanically fastened synthetic roof underlayment engineered by Innoflex Synthetics to deliver enhanced durability and long-term protection for steep-slope roofing systems. Manufactured in North America, it features a rugged 20-mil construction that blends advanced woven and non-woven layers for superior tear strength, dimensional stability, and superior walkability in all weather conditions.

**STORMFLEX ELITE™** is designed for use under asphalt shingles, concrete and clay tiles, all metal panels, synthetic shingles and primed cedar shakes. **STORMFLEX ELITE™** meets all the code requirements including ASTM D226, ASTM 48D69 and AC 188 as required by ICC-ES.

## FEATURES & BENEFITS

- Superior traction surface combined with slip resistant bottom coating provides unmatched walkability in dry, wet, or cold conditions.
- All weather performance (-40F to 240F)
- Eco-Smart Construction: 100% Recyclable Polypropylene Base
- Extended UV Exposure Rating: 180 days
- Limited Lifetime Warranty
- Meets/Exceeds: ASTM D4869: ASTM D8257: CAN/CSA A123.3
- FBC & IRBC Approved
- Custom Dual Logo Printing Available

### Test/Standard

### Typical Value

|                               |                                           |
|-------------------------------|-------------------------------------------|
| Roll Width                    | 48" / 1.22 m                              |
| Roll Length                   | 250' / 76.2 m                             |
| Roll Weight                   | 35.0 lb / 15.9 kg                         |
| Rolls/Pallet/Truck            | 36 / 1692 rolls                           |
| Tensile Strength (ASTM D5034) | MD 141 lb (64.0 kg)   CD 127 lb (57.6 kg) |
| Tear Strength (ASTM D4533)    | MD 29 lb (13 kg)   CD 24 lb (11 kg)       |
| UV Exposure (ASTM D8257)      | 180 Days                                  |
| Temp Range                    | -40°C to 115°C / -40°F to 240°F           |

The data shown above is based on lab test averages from production runs. Values are typical data and not limiting specifications. All values are +/-10% variation. This report should not be considered as a warranty. The manufacturer is not responsible for the misrepresentation or misinterpretation of the data by the reader.



Innoflex Synthetics Ltd. | 3855 Mt. Lehman Rd. Abbotsford, BC V2T 5W5 | [info@innoflexsyn.com](mailto:info@innoflexsyn.com)